





Peel-Type Blind Rivets

Manufacturer: RivetFast



Materials

Body	Aluminum Alloy
Body	Stainless Steel
Body	Steel

d	$l$ +0.99	dk	Hole	Min. Grip	Max. Grip	K (k2)	L1	Minimum Tensile Strength (N)	Minimum shear Strength (N)
Φ3.2±0.09	8	Φ6.0±0.24	Φ3.4	0.5	1.0	1.4(1.2)	26	700	765
Φ3.2±0.09	10	Φ6.0±0.24	Φ3.4	1.0	3.0	1.4(1.2)	26	700	765
Φ3.2±0.09	12	Φ6.0±0.24	Φ3.4	3.5	5.0	1.4(1.2)	26	700	765
Φ4.0±0.09	10	Φ8.0±0.29	Φ4.2	1.5	5.0	1.7(1.4)	27	1150	1260
Φ4.0±0.09	12	Φ8.0±0.29	Φ4.2	4.0	6.5	1.7(1.4)	27	1150	1260
Φ4.0±0.09	14	Φ8.0±0.29	Φ4.2	6.0	9.0	1.7(1.4)	27	1150	1260
Φ4.0±0.09	16	Φ8.0±0.29	Φ4.2	8.0	11.0	1.7(1.4)	27	1150	1260
Φ4.8±0.09	10	Φ9.5±0.29	Φ5.0	0.5	4.0	2(1.6)	27	1600	1855
Φ4.8±0.09	12	Φ9.5±0.29	Φ5.0	2.0	6.0	2(1.6)	27	1600	1855
Φ4.8±0.09	14	Φ9.5±0.29	Φ5.0	4.0	8.0	2(1.6)	27	1600	1855
Φ4.8±0.09	16	Φ9.5±0.29	Φ5.0	6.0	10.0	2(1.6)	27	1600	1855
Φ4.8±0.09	18	Φ9.5±0.29	Φ5.0	8.0	12.0	2(1.6)	27	1600	1855
Φ4.8±0.09	20	Φ9.5±0.29	Φ5.0	10.0	14.0	2(1.6)	27	1600	1855
Φ4.8±0.09	22	Φ9.5±0.29	Φ5.0	12.0	16.0	2(1.6)	27	1600	1855
Φ4.8±0.09	24	Φ9.5±0.29	Φ5.0	14.0	18.0	2(1.6)	27	1600	1855
Φ4.8±0.09	26	Φ9.5±0.29	Φ5.0	16.0	20.0	2(1.6)	27	1600	1855